

Test Report

No. SH8039578-1/CHEM

Date: Apr. 11, 2008

Page 1 of 4

HANGZHOU NEW LINE CO., LTD
RM.60H, NO.1 GUODU DEVELOPMENT BLDG., NO.182 ZHAOHUI ROAD, HANGZHOU ZHEJIANG CHINA

THIS REPORT IS TO SUPERSEDE TEST REPORT NO.SH8039578/CHEM DATE: 2008/03/28

The following sample(s) was/were submitted and identified by/on behalf of the client as:

Sample Name : SALT & PEPPER SHAKER
SGS Ref No. : SHD2804016
Country of Origin : CHINA
Country of Destination : USA

Sample Receiving Date : Mar.25, 2008
Testing Period : Mar.25 – 28, 2008

Test Requested : (1) As specified for client, for compliance with the Food and Drug Administration Regulations for polypropylene used in contact with food.
(2) As specified by the client, for compliance with Food and Drug Administration Regulations for determining acrylonitrile monomer content for finished food-contact articles containing acrylonitrile copolymers and resins

Test Method : (1) As specified in FDA 21 CFR 177.1520(c)(3.1)
(2) With reference to FDA 21 CFR 180.22 & 181.32.

Test Results : Please refer to next page

Conclusion : (1) The submitted Gray plastic part samples said to be used for SALT & PEPPER SHAKER comply with the FDA Specifications for polyolefin co-polymer used in articles that contact with food and packing or holding food during cooking.
(2) The submitted plastics samples said to be used for SALT & PEPPER SHAKER comply with the FDA Specifications for determining acrylonitrile monomer content for finished food-contact articles containing acrylonitrile copolymers and resins.

Signed for and on behalf of
SGS-CSTC Chemical Laboratory



Ella Zhang
Section Manager

Signed for and on behalf of
SGS-CSTC Chemical Laboratory



Sandy Hao
Lab Manager

Test Report

No. SH8039578-1/CHEM

Date: Apr. 11, 2008

Page 2 of 4

Test Results :

(1) FDA 21 CFR 177.1520(c)(3.1)

	1. <u>Gray plastic part</u>	<u>Limit</u>
1. Density at 23°C , g / mL	0.917	0.850 – 1.000
2. Extractable fraction in n-hexane at reflux temperature , W/W %	3.0	5.5max (contact with food)
3. Soluble fraction in xylene at 25°C , W/W %	6.0	30.0 max.

Note : < = Less than

(2) FDA 21 CFR 180.22 & 181.32


<u>Extractants and Conditions</u>	<u>2**. Transparent plastic part Acrylonitrile monomer Content (mg/inch²)</u>	<u>Maximum permissible Limit (mg/inch²)</u>
1. Distilled Water 120°F for 24 hours	<0.001	0.003
2. 8% Alcohol at 120°F for 24 hours	<0.001	0.003
3. 3% acetic acid at 120°F for 24 hours	<0.001	0.003
4. n-Heptane at 120°F for 24 hours	<0.001	0.003

Note: **The test results are taken from report SH8029510/CHEM, Date: 2008/03/19.

Test Part Description:


1. Gray plastic part
2. Transparent plastic part

Sample Photo:



The content of this PDF file is in accordance with the original issued reports for reference only. This Test Report cannot be reproduced, except in full, without prior written permission of the Company.





SGS authenticate the photo on original report only

*** End of Report ***