



Test Report

Number: SHAH00450279

Applicant: HANGZHOU NEW LINE CO.,LTD
RM.60H, NO.1 GUODU DEVELOPMENT BLDG,
NO.182 ZHAOHUI ROAD, HANGZHOU ZHEJIANG
Attn: JENNY

Date: APR 29, 2014

Sample Description:

Five(5) pieces of submitted samples said to be **Black Plastic Tent Stake.**

Item Name : Plastic Tent Stake.

Goods Exported To : USA.

Country Of Origin : China.

Tests Conducted:

As requested by the applicant, for details refer to attached page(s).

Conclusion:

Tested Component

Standard

Result

Tested Component

Total Lead Content

See test conducted

Total Cadmium Content

See test conducted

Total Chromium Content

See test conducted

Total Mercury Content

See test conducted

Total Nickel Content

See test conducted

To be continued

Authorized By:

For Intertek Testing Services Ltd., Shanghai

Leo Shi
General Manager



Intertek Testing Services Ltd., Shanghai

Block B, Jinling Business Square, No.801 YiShan Road, Shanghai, China. 200233

上海天祥質量技術服務有限公司

上海市宜山路 801 號金陵商務廣場 B 座 200233

Telephone: +86 21 6120 6060 Facsimile: +86 21 6127 9740

www.intertek.com www.intertek.com.cn

Tests Conducted

1 Total Lead (Pb) Content

As per client's request, acid digestion method was used and total Lead content was determined by Inductively Coupled Argon Plasma Spectrometry.

Result : <10 ppm

Remark: ppm = Parts per million = mg/kg

Tested Component: Black Plastic.

2 Total Cadmium (Cd) Content

As per client's request, acid digestion method was used and total Cadmium content was determined by Inductively Coupled Argon Plasma Spectrometry.

Result : <5 ppm

Remark: ppm = Parts per million = mg/kg

Tested Component :Black Plastic.

3 Total Chromium (Cr) Content

As per client's request, acid digestion method was used and total Chromium content was determined by Inductively Coupled Argon Plasma Spectrometry.

Result : <5 ppm

Remark: ppm = Parts per million = mg/kg

Tested Component: Black Plastic.

4 Total Mercury Content

As per client's request, acid digestion method was used and total Mercury content was determined by Inductively Coupled Argon Plasma Spectrometry.

Result : <5 ppm

Remark: ppm = Parts per million = mg/kg

Tested Component: Black Plastic.

To be continued

Tests Conducted

5 Total Nickel (Ni) Content

As per client's request, acid digestion method was used and total Nickel content was determined by Inductively Coupled Argon Plasma Spectrometry.

Result : <5 ppm

Remark: ppm = Parts per million = mg/kg

Tested Component: Black Plastic.



Picture of sample

Date Sample Received: Apr.23, 2014

Testing Period: Apr.23, 2014 To Apr.29, 2014

End of report

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or wilful misconduct.